

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2003-209046

(43)Date of publication of application : 25.07.2003

(51)Int.Cl.

H01L 21/027

G03F 7/004

G03F 7/11

G03F 7/38

H01L 21/3065

(21)Application number : 2002-007228 (71)Applicant : MITSUBISHI ELECTRIC CORP


(22)Date of filing : 16.01.2002 (72)Inventor : KAWAI KENJI

(54) RESIST PATTERN FORMING METHOD AND SEMICONDUCTOR DEVICE MANUFACTURING METHOD

(57)Abstract:

PROBLEM TO BE SOLVED: To form a resist pattern with high accuracy even on an underlayer film including a basic substance by controlling an oxygen deficiency/activity phenomenon at the interface between the underlayer film including a basic substance and a chemically amplified resist formed thereon.

SOLUTION: This method comprises a step for performing a surface reforming process to expose the underlayer film surface including the basic substance to the plasma of gas including carbon gas, a step for coating the chemically amplified resist film of the underlayer film, and a step for patterning the chemically amplified resist through the exposing and development processes thereof.



LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other

than the examiner's decision of rejection or
application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's
decision of rejection]

[Date of requesting appeal against
examiner's decision of rejection]

[Date of extinction of right]

* NOTICES *

JPO and NCIPi are not responsible for any damages caused by the use of this translation.

- 1.This document has been translated by computer. So the translation may not reflect the original precisely.
- 2.**** shows the word which can not be translated.
- 3.In the drawings, any words are not translated.

CLAIMS

[Claim(s)]

[Claim 1] The resist pattern formation approach equipped with surface down stream processing which exposes the substrate film front face containing an alkali into the plasma using the gas containing carbon, the process which forms a chemistry magnification mold resist on said substrate film by which surface preparation was carried out, and the process which performs exposure and a development to said chemistry magnification mold resist, and carries out patterning of said chemistry magnification mold resist.

[Claim 2] The gas containing carbon is the resist pattern formation approach according to claim 1 characterized by being fluorocarbon, hydro fluorocarbon, a hydrocarbon, hexamethyldisilazane, CO and CO₂, and gas containing at least one or more of R-OH (alcohols).

[Claim 3] The substrate film is the resist pattern formation approach according to claim 1 characterized by including at least one or more of SiON, and SiN, TiN, WN, TaN, BN, CN(s), AlN(s), GaN(s) and GeN(s).

[Claim 4] The substrate film is the resist pattern formation approach according to claim 1 characterized by being the antireflection film.

[Claim 5] The resist pattern formation approach equipped with surface down stream processing which exposes the substrate film front face containing an alkali to ozone gas, the process which forms the chemistry magnification mold resist film on said substrate film by which surface preparation was carried out, and the process which performs exposure and a development to said chemistry magnification mold resist, and carries out patterning of said chemistry magnification mold resist.

[Claim 6] The resist pattern formation approach equipped with surface down stream processing which exposes the substrate film front face containing an alkali to the elevated-temperature gas containing oxygen, the process which forms the chemistry magnification mold resist film on said substrate film by which surface preparation was carried out, and the process which performs exposure and a development to said chemistry magnification mold resist, and carries out patterning of said chemistry magnification mold resist.

[Claim 7] The elevated-temperature gas containing oxygen is the resist pattern formation approach according to claim 6 characterized by being N₂O or O₂.

[Claim 8] The resist pattern formation approach which is the resist pattern formation approach equipped with the process which forms the substrate film containing an alkali on a substrate, the process which form the chemistry magnification mold resist film on said substrate film, and the process which perform exposure and a development to said chemistry magnification mold resist, and carry out patterning of said chemistry magnification mold resist, and is characterized by to perform said exposure where it gave potential to said substrate with an electrical-potential-difference impression means and polarization of said substrate film is carried out.

[Claim 9] An electrical-potential-difference impression means is the resist pattern formation approach according to claim 8 characterized by being high-frequency voltage.

[Claim 10] An electrical-potential-difference impression means is the resist pattern formation approach according to claim 8 characterized by giving potential to this base through the stage in which the substrate was laid.

[Claim 11] The manufacture approach of the semiconductor device equipped with the process which

etches the substrate film using the resist pattern formed using claim 1 thru/or the resist pattern formation approach given in ten.

[Translation done.]

* NOTICES *

JPO and NCIPi are not responsible for any damages caused by the use of this translation.

1. This document has been translated by computer. So the translation may not reflect the original precisely.
2. **** shows the word which can not be translated.
3. In the drawings, any words are not translated.

DETAILED DESCRIPTION

[Detailed Description of the Invention]

[0001]

[Field of the Invention] This invention relates to the resist pattern formation approach for precision to improve a chemistry magnification mold resist patterning on the substrate film which contains an alkali especially about the manufacture approach of a semiconductor device of having used the resist pattern formation approach and this, and the manufacture approach of the semiconductor device using this approach.

[0002]

[Description of the Prior Art] Drawing 10 and drawing 11 are the sectional views showing the manufacture approach of the conventional semiconductor device of having used the chemistry magnification mold resist. With reference to drawing 10 (a), sequential formation of the processed film 103, the antireflection film 105, and the chemistry magnification mold resist 107 of a positive type is carried out on the semi-conductor substrate 101. Next, with reference to drawing 10 (b), the excimer laser light 111 is irradiated through the photo mask 109 which arranged the desired pattern on the semi-conductor substrate 101, and the chemistry magnification mold resist 107 is exposed. At this time, H⁺ which is proton acid occurs within the chemistry magnification mold resist 107 in exposure section 107a by which light was irradiated. Resist resin etc. acts as a catalyst which causes a chemical change, and this proton acid is changed to the matter which dissolves in a developer.

[0003] Next, by developing the exposed chemistry magnification mold resist 107 with reference to drawing 10 (c), exposure section 107a is dissolved and resist pattern 107c is formed because unexposed part 107b remains. Next, antireflection-film pattern 105b is formed by etching the antireflection film 105 by using resist pattern 107c as a mask with reference to drawing 11 (a).

[0004] Next, with reference to drawing 11 (b), the processed film 103 is etched into a mask for resist pattern 107c and antireflection-film pattern 105b, and desired processed film pattern 103a is obtained. Then, a resist pattern is removed and a desired semiconductor device is completed through a predetermined process.

[0005]

[Problem(s) to be Solved by the Invention] However, in the above conventional techniques, if the antireflection film which is substrate film of a chemistry magnification mold resist contains the alkali which is easy to give an electron, as shown in drawing 12, in the interface of a resist and the antireflection film, the solubility to the developer of a resist will fall according to the so-called acid deactivation phenomenon of causing the electron with which the proton acid (H⁺) generated in the resist was supplied from the antireflection film, and neutralization.

[0006] Consequently, as shown in drawing 10 (c), it becomes the configuration in which the lower part of resist pattern 107c lengthened the skirt. There was a trouble that a processed film pattern would become thicker than a desired dimension, or would become the stage gap configuration where the shoulder fell, and control of dimensional accuracy would become difficult about such a resist pattern if the processed film is etched into a mask. In addition, in the case of a negative mold (an unexposed part dissolves in a developer), although the chemistry magnification mold resist mentioned above assumed the positive type (the exposure section dissolves in a developer), the lower part of a resist pattern became thin conversely, consequently that a resist pattern tends to fall, it became and there were same troubles -- a processed film pattern becomes thin.

[0007] Made in order that the invention in this application might solve the above problems, the 1st purpose offers the resist pattern formation approach which can form an accurate resist pattern also on the substrate film containing an alkali.

[0008] Moreover, the 2nd purpose offers the manufacture approach of a semiconductor device of having used the above-mentioned resist pattern formation approach.

[0009]

[Means for Solving the Problem] It has the process which performs exposure and a development to the process and chemistry magnification mold resist which form a chemistry magnification mold resist on the substrate film by which surface preparation was carried out to surface down stream processing which exposes the substrate film front face containing an alkali into the plasma using the gas containing carbon, and carries out patterning of the chemistry magnification mold resist.

[0010] Moreover, let the gas containing carbon be fluorocarbon, hydro fluorocarbon, a hydrocarbon, hexamethyldisilazane, CO and CO₂, and gas containing at least one or more of R-OH (alcohols).

[0011] Moreover, it is made for the substrate film to contain at least one or more of SiON, and SiN, TiN, WN, TaN, BN, CN(s), AlN(s), GaN(s) and GeN(s).

[0012] Moreover, let the substrate film be an antireflection film.

[0013] Moreover, it has the process which performs exposure and a development to the process and chemistry magnification mold resist which form the chemistry magnification mold resist film on the substrate film by which surface preparation was carried out to surface down stream processing which exposes the substrate film front face containing an alkali to ozone gas, and carries out patterning of the chemistry magnification mold resist.

[0014] Moreover, it has the process which performs exposure and a development to the process and chemistry magnification mold resist which form the chemistry magnification mold resist film on the substrate film by which surface preparation was carried out to surface down stream processing which exposes the substrate film front face containing an alkali to the elevated-temperature gas containing oxygen, and carries out patterning of the chemistry magnification mold resist.

[0015] Moreover, the elevated-temperature gas containing oxygen is set to N₂O or O₂.

[0016] Moreover, it has the process which performs exposure and a development to the process which forms the substrate film containing an alkali on a substrate, the process which forms the chemistry magnification mold resist film on the substrate film, and a chemistry magnification mold resist, and carries out patterning of the chemistry magnification mold resist, and it is made to expose, where it gave potential to the substrate with the electrical-potential-difference impression means and polarization of the substrate film is carried out.

[0017] Moreover, let an electrical-potential-difference impression means be high-frequency voltage.

[0018] Moreover, an electrical-potential-difference impression means gives potential to this base through the stage in which the substrate was laid.

[0019] Moreover, the substrate film is etched using the above-mentioned approach.

[0020]

[Embodiment of the Invention] Gestalt 1. drawing 1 thru/or drawing 3 of operation is the outline sectional view showing the production process of the semiconductor device concerning the gestalt 1 of operation of the invention in this application. In addition, in the following explanation, the sign identically same into a considerable part is attached, and the explanation is omitted.

[0021] With reference to drawing 1 (a), on the semi-conductor substrate 1, the mixed gas of SiH₄ (silane) and H₂ (hydrogen) or the mixed gas of SiH₄ and N₂ (nitrogen) is used, and the processed film 3 which consists of polish recon under 600 degrees C - 700 degrees C formation temperature conditions is formed with a reduced pressure CVD method. You may make it diffuse an impurity by heat treatment at this time, using PH₃ and AsH₃ as a source of an impurity. Next, on this processed film 3, by the plasma-CVD method, the mixed gas of SiH₄, NH₃ (ammonia), and N₂O (dinitrogen oxide) is used, and the matter 5 in which basicity is shown under 300 degrees C - 450 degrees C formation temperature conditions, for example, the antireflection film which consists of SiON (acid silicon nitride) containing N, is formed.

[0022] As an antireflection film 5 in which basicity is shown, SiN (silicon nitride), TiN (titanium nitride), etc. may be used other than above SiON. SiN is formed by the plasma-CVD method using the mixed gas of SiH₄, NH₃, and H₂ under 300 degrees C - 450 degrees C formation temperature

conditions.

[0023] Next, the gas containing C (carbon) is plasma-ized with reference to drawing 1 (b), and the front face of an antireflection film 5 is reformed by exposing the semi-conductor substrate 1 to this plasma 2. The plasma 2 makes the gas which contains C under the pressure of 1.33Pa - 133Pa discharge using an ICP mold plasma reactor or 2 cycle parallel monotonous mold plasma reactor, and is formed. The time amount exposed to the plasma 2 is 5 seconds - a 30-second about room. Of this surface treatment, the reforming layer 4 which consists of a CF system polymer (CxFy) with a thickness of 1-20nm is formed in the front face of an antireflection film 5.

[0024] As gas containing C, the gas containing fluorocarbon system gas, hydro fluorocarbon system gas, hydrocarbon system gas, HMDS (hexamethyldisilazane: (CH₃)₃Si₂NH₂), CO (carbon dioxide gas) and CO₂ (carbon dioxide), and at least one or more R-OH (alcohols) [R:alkyl group] is used, for example.

[0025] Here, fluorocarbon system gas is CF₄ (tetra-FURORO methane), C₄F₈ (OKUTAFURORO cyclobutane), C₅F₈ (OKUTAFURORO cyclopentene), C₄F₆ (hexa FURORO -1, 3-butadiene), C₂F₆ (hexa FURORO ethane), C₃F₈ (OKUTAFURORO propane), etc. Moreover, hydro fluorocarbon system gas is CHF₃ (TORIFURORO methane), CH₂F₂ (JIFURORO methane), CH₃F (mono-FURORO methane), etc. Moreover, hydrocarbon system gas is CH₄ (methane), C₂H₂ (acetylene), C₂H₄ (ethylene), etc.

[0026] Next, with reference to drawing 1 (c), the chemistry magnification mold resist film 7 of 500nm of thickness is formed on the antireflection film 5 with which the reforming layer 4 was formed in the front face. As chemistry magnification mold resist film 7, the commercial positive resist (TDUR-P015: TOKYO OHKA KOGYO make) was used. Next, with reference to drawing 2 (a), through the photo mask 9 which arranged the desired pattern, the excimer laser light 11, such as KrF (wavelength of 248nm) and ArF (wavelength of 193nm), is irradiated, and the chemistry magnification mold resist 7 is exposed on the semi-conductor substrate 1.

[0027] Although proton acid (H⁺) arises in exposure partial 7a of a resist as a catalyst which promotes a chemical change at this time, the reforming layer 4 formed in the front face of the antireflection film 5 which is substrate film turns into a block layer which blocks supply of the electron from the antireflection film 5, and the neutralization (acid deactivation phenomenon) in the interface of a resist and the antireflection film is controlled.

[0028] Consequently, with reference to drawing 2 (b), in a subsequent development, the solubility to the developer of exposure partial 7a improves, and resist pattern 7c in which unexposed part part 7b is formed by remaining becomes a good configuration without skirt length. Moreover, an antireflection-film front face serves as hydrophobicity by the above surface preparation, and the adhesion of a resist and the antireflection film also improves.

[0029] Next, with reference to drawing 2 (c), using the plasma of the mixed gas of CF₄, O₂, and Ar which were controlled by 2 cycle parallel monotonous mold etching system by the pressure of 10mTorr - 800mTorr in resist pattern 7c at the mask, the reforming layer 4 and the antireflection film 5 are etched, and antireflection-film pattern 5a is formed. In addition, the mixed gas which added CHF₃ gas further may be used for the above-mentioned mixed gas.

[0030] Next, with reference to drawing 3, the processed film 3 is etched using the plasma of the mixed gas of Cl₂ and O₂ controlled by the ICP mold or the ECR mold etching system by the pressure of 0.2-10Pa at the mask in resist pattern 7c and antireflection-film pattern 5a, or the mixed gas of HBr and O₂, and processed film pattern 3a is formed. Then, resist pattern 7c which became unnecessary is removed, and a desired semiconductor device is completed through a predetermined process.

[0031] As mentioned above, according to invention concerning the gestalt 1 of operation, by exposing the antireflection-film front face containing the alkali used as the substrate in which a chemistry magnification mold resist should be formed to the plasma using the gas containing C, since the neutralization in the interface of the antireflection film and a chemistry magnification mold resist is controlled in the case of the exposure in chemistry magnification mold resist pattern formation, a resist pattern with a good configuration is obtained.

[0032] Moreover, since the adhesion of a chemistry magnification mold resist and the antireflection film improves by the above-mentioned plasma treatment, prevention ***** can perform resist

peeling. Consequently, the etching controllability of the processed film which used the chemistry magnification mold resist pattern as the mask can improve, and a semiconductor device with the good high processed **** pattern of a dimensional accuracy controllability can be manufactured.

[0033] Although plasma treatment which contains C in the substrate film containing an alkali was performed and the front face was reformed with the gestalt 1 of gestalt 2. implementation of operation, the gestalt of this operation is related with the surface treatment approach with few damages than the plasma. Drawing 4 thru/or drawing 6 are the outline sectional views showing the production process of the semiconductor device concerning the gestalt 2 of operation of the invention in this application. Hereafter, it explains to a detail using these drawings.

[0034] With reference to drawing 4 (a), sequential formation of the antireflection films 5, such as SiON containing an alkali, is carried out like the gestalt 1 of operation as the processed film 3 which consists of polish recon on the semi-conductor substrate 1, and substrate film. Next, with reference to drawing 4 (b), the front face of the antireflection film 5 on the semi-conductor substrate 1 is exposed to O₃ (ozone) gas 6, and the front face of an antireflection film 5 is reformed.

[0035] O₃ gas 6 lays the semi-conductor substrate 1 using a predetermined processor on the stage set as the temperature of 20 degrees C - 200 degrees C, is in the condition which maintained the pressure in equipment at 100mTorr(s) - 10Torr, and is introduced to the front face of the semi-conductor substrate 1 by the force of exhaust air of the ozone gas which occurred in OZONETA. The reforming layer 8 which becomes the front face of an antireflection film 5 from an oxide film (SiO_x (0 < x < 2)) with a thickness of 1nm - 10nm by such surface treatment is formed.

[0036] Next, with reference to drawing 4 (c), the chemistry magnification mold resist film 7 of the positive type of 500nm of thickness is formed on the antireflection film 5 with which the reforming layer 8 was formed in the front face. Next, with reference to drawing 5 (a), through the photo mask 9 which arranged the desired pattern, the excimer laser light 11, such as KrF (248nm) and ArF (193nm), is irradiated, and the chemistry magnification mold resist 7 is exposed on the semi-conductor substrate 1.

[0037] Although proton acid (H⁺) arises in exposure section 7a of a resist as a catalyst which promotes a chemical change at this time, the reforming layer 8 formed in the front face of the antireflection film 5 which is substrate film turns into a block layer which blocks supply of the electron from the antireflection film 5, and the neutralization (acid deactivation phenomenon) in the interface of a resist and the antireflection film is controlled.

[0038] Consequently, with reference to drawing 5 (b), in a subsequent development, the solubility to the developer of exposure section 7a improves, and resist pattern 7c in which unexposed part 7b is formed by remaining becomes a good configuration without skirt length. Moreover, since a semi-conductor substrate is only exposed to a gas ambient atmosphere, like [when performing plasma treatment], there are few charge-up damages by the plasma, and they can prevent destruction of gate dielectric film etc.

[0039] Hereafter, like the case of the gestalt 1 of operation, with reference to drawing 5 (c), the reforming layer 8 and the antireflection film 5 are etched into a mask for resist pattern 7c, and antireflection-film pattern 5a is formed. Then, with reference to drawing 6, the processed film 3 is etched into a mask for resist pattern 7c and antireflection-film pattern 5a, and processed film pattern 3a is formed. Resist pattern 7c which became unnecessary at the end is removed, and a semiconductor device is completed through a predetermined process.

[0040] As mentioned above, according to invention concerning the gestalt 2 of operation, by exposing the antireflection-film front face containing the alkali used as the substrate in which a chemistry magnification mold resist should be formed to O₃ gas, the neutralization in the interface of the antireflection film and a chemistry magnification mold resist is controlled in the case of the exposure at the time of chemistry magnification mold resist pattern formation, and a resist pattern with a good configuration is obtained. Consequently, the etching controllability of the processed film which used this resist pattern as the mask can improve, and a semiconductor device with the good high processed **** pattern configuration of a dimensional accuracy controllability can be manufactured.

[0041] Moreover, since a reforming layer is formed only by exposing to O₃ gas, when plasma treatment is performed, the charge-up damage by the plasma can be reduced like, and a reliable

semiconductor device can be manufactured.

[0042] Although the antireflection film front face which is the substrate of a chemistry magnification mold resist was reformed by ozone gas with the gestalt 2 of gestalt 3. implementation of operation, elevated-temperature gas, such as N₂O containing oxygen and O₂, is used instead of ozone gas with the gestalt of this operation. Other processes are the same as the gestalt 2 of operation. Using a predetermined processor, such elevated-temperature gas lays the semi-conductor substrate 1 on a stage, and is introduced to the front face of the semi-conductor substrate 1 by the force of exhaust air of the above-mentioned gas heated to the 600 degrees C - 1000 degrees C elevated temperature with the fission reactor where the pressure in equipment is maintained at 100mTorr(s) - 10Torr.

[0043] As mentioned above, according to invention concerning the gestalt 3 of operation, by exposing the antireflection film front face containing the alkali used as the substrate in which a chemistry magnification mold resist should be formed to elevated-temperature gas, such as OON22 gas containing oxygen, the neutralization in the interface of an antireflection film and a chemistry magnification mold resist is controlled in the case of the exposure at the time of chemistry magnification mold resist pattern formation, and a resist pattern with a good configuration is obtained. Consequently, the etching controllability of the processed film which used this resist pattern as the mask can improve, and a semiconductor device with the good high processed **** pattern configuration of a dimensional accuracy controllability can be manufactured.

[0044] Furthermore, since a reforming layer is formed only by exposing to OON22 gas, when plasma treatment is performed, the charge-up damage by the plasma can be reduced like, and a reliable semiconductor device can be manufactured.

[0045] In the gestalt 1 of gestalt 4. implementation of operation thru/or 3, neutralization of the proton acid in the resist generated near an interface with the substrate film (H⁺) is controlled by forming a reforming layer in the substrate film front face containing an alkali, and giving an electric action to a semi-conductor substrate with the gestalt of this operation, although neutralization was controlled by blocking supply of the electron from the substrate film to a resist.

[0046] Drawing 7 and drawing 8 are the outline sectional views showing the production process of the semiconductor device concerning the gestalt 3 of operation of the invention in this application. With reference to drawing 7 (a), sequential formation of the antireflection films 5, such as SiON containing an alkali, is carried out as the processed film 3 which consists of polish recon on the semi-conductor substrate 1, and substrate film. Next, with reference to drawing 7 (b), the chemistry magnification mold resist film 7 is formed on the antireflection film 5.

[0047] Next, with reference to drawing 7 (c), through the photo mask 9 which arranged the desired pattern, the excimer laser light 11, such as KrF (248nm) and ArF (193nm), is irradiated, and the chemistry magnification mold resist 7 is exposed on the semi-conductor substrate 1. At this time, forward predetermined potential is given to the semi-conductor substrate 1 by the electrical-potential-difference impression means 10. Potential may be directly given to the semi-conductor substrate 1, and may be indirectly given by impressing an electrical potential difference to stages, such as semiconductor fabrication machines and equipment with which the semi-conductor substrate 1 is laid.

[0048] Drawing 9 is the fragmentary sectional view of the semiconductor device which shows the appearance of the charge in the antireflection film 5 at the time of giving forward potential typically to a semi-conductor substrate. If forward potential is given to the semi-conductor substrate 1 with reference to drawing 9, the charge in an antireflection film 5 will polarize and negative charge (electron) will gather for positive charge and its opposed face in a front face. In this condition, exposure of the chemistry magnification mold resist 7 generates proton acid (H⁺) in exposure section 7a as a catalyst which promotes a chemical reaction. On the other hand, the electron in it polarizes the basic antireflection film 5 as mentioned above, it will be in the condition that the trap was carried out so to speak, and the basic property to supply an electron will become weaker.

[0049] Consequently, as supply of the electron from the antireflection film 5 decreases, neutralization with the proton acid in a resist (H⁺) and an electron is controlled and it is shown in drawing 8 (a), in a subsequent development, the solubility to the developer of exposure section 7a improves, and resist pattern 7c in which unexposed part 7b is formed by remaining becomes a good configuration without skirt length.

[0050] Hereafter, like the gestalt 1 of operation, with reference to drawing 8 (b), the antireflection film 5 is etched into a mask for resist pattern 7c, and antireflection-film pattern 5a is formed. Next, with reference to drawing 8 (c), the processed film 3 is etched into a mask for resist pattern 7c and antireflection-film pattern 5a, and processed film pattern 3a is formed. Then, resist pattern 7c which became unnecessary is removed, and a semiconductor device is completed through a predetermined process.

[0051] In addition, since the proton acid in a resist (H^+) will be opposed with the positive charge which polarized and gathered in the antireflection-film front face and the catalytic reaction in a resist pars basilaris ossis occipitalis will fall if too not much strong, the forward potential given by the electrical-potential-difference impression means 10 has a possibility that a configuration may get worse on the contrary. Therefore, the forward potential given is large to extent which can carry out the trap of the electron, it is necessary to be potential small to extent which does not repel proton acid (H^+), and its potential which is +100V-1000V is desirable.

[0052] Moreover, although applied voltage was forward direct current voltage in the above-mentioned example, high-frequency voltage is impressed, and the same effectiveness is done so even if proton acid (H^+) moves near an interface with an antireflection film in the inside of resist exposure section 7a, vibrating up and down. It is desirable that it is 100kHz - 20MHz H^+ ion which is proton acid follows in whose footsteps as a RF.

[0053] As mentioned above, since the property as basicity in which the trap of the electron in an antireflection film is carried out, and it supplies the electron of an antireflection film by giving forward potential to a semi-conductor substrate becomes weaker according to invention concerning the gestalt 4 of operation, deactivation of the proton acid in a chemistry magnification mold resist (H^+) is controlled, and a resist pattern with a good configuration is obtained. Consequently, the etching controllability of the processed film which used this resist pattern as the mask can improve, and a semiconductor device with the good high processed **** pattern configuration of a dimensional accuracy controllability can be obtained.

[0054] In addition, although the case where the substrate film in which basicity is shown was an antireflection film was assumed with the gestalt of each operation mentioned above, if it is the substrate film in which it is not necessarily restricted to this and basicity is shown including an alkali, applying on any substrate film is possible. For example, it is applicable also on the ingredient which contains N, such as BN (boron nitride), CN (nitriding carbon), AlN (aluminum nitride), GaN (gallium nitride), and GeN (nitriding germanium), as TiN, WN (nitriding tungsten) and TaN (tantalum nitride) as barrier metal film, and film of the other application. Moreover, although the chemistry magnification mold resist assumed the case where it was a positive type, even if it is a negative mold, it cannot be overemphasized that the same effectiveness is done so.

[0055]

[Effect of the Invention] Since this invention is constituted as mentioned above, it does effectiveness as taken below so. Since surface preparation of the substrate film front face containing an alkali is carried out with the gas plasma containing carbon according to invention concerning claim 1, precision can improve [patterning] the chemistry magnification mold resist formed on it.

[0056] Moreover, according to invention concerning claim 2, further, the adhesion of the substrate film and a chemistry magnification mold resist can improve, and resist peeling can be prevented.

[0057] Moreover, according to invention concerning claim 3, a resist pattern with a precision high also on substrate film like SiON, and SiN, TiN, WN, TaN, BN, CN, AlN, GaN and GeN can be formed.

[0058] Moreover, according to invention concerning claim 4, further, since reflection of exposure light can be prevented, a resist pattern with a more high precision can be formed.

[0059] Moreover, since the substrate film front face containing an alkali is exposed to ozone gas according to invention concerning claim 5, while precision can improve [patterning] the chemistry magnification mold resist formed on it, since the damage to the substrate film can be lessened, reliable patterning can be carried out.

[0060] Moreover, since the substrate film front face containing an alkali is exposed to the elevated-temperature gas containing oxygen according to invention concerning claim 6, while precision can improve [patterning] the chemistry magnification mold resist formed on it, since the damage to the

substrate film can be lessened, reliable patterning can be carried out.

[0061] Moreover, according to invention concerning claim 7, a chemistry magnification mold resist can be formed with a sufficient precision using N₂O or simple gas like O₂ as elevated-temperature gas.

[0062] Moreover, since the substrate film which gives forward potential to a substrate and contains an alkali is polarized according to invention concerning claim 8, precision can improve [patterning] the chemistry magnification mold resist formed on it.

[0063] Moreover, according to invention concerning claim 9, further, since the controllability of applied voltage improves, patterning of the stable chemistry magnification mold resist can be carried out.

[0064] Moreover, according to invention concerning claim 10, patterning of an accurate chemistry magnification mold resist can be carried out using the existing semiconductor fabrication machines and equipment.

[0065] Moreover, according to invention concerning claim 11, since the processed film can be etched into a mask, the etching controllability of the processed film can improve an accurate resist pattern, and a semiconductor device with the good high processed **** pattern configuration of a dimensional accuracy controllability can be obtained.

[Translation done.]

* NOTICES *

JPO and NCIPi are not responsible for any damages caused by the use of this translation.

1. This document has been translated by computer. So the translation may not reflect the original precisely.
2. **** shows the word which can not be translated.
3. In the drawings, any words are not translated.

DESCRIPTION OF DRAWINGS

[Brief Description of the Drawings]

- [Drawing 1] It is the outline sectional view showing the production process of the semiconductor device concerning the gestalt 1 of operation of the invention in this application.
- [Drawing 2] It is the outline sectional view showing the production process of the semiconductor device concerning the gestalt 1 of operation of the invention in this application.
- [Drawing 3] It is the outline sectional view showing the production process of the semiconductor device concerning the gestalt 1 of operation of the invention in this application.
- [Drawing 4] It is the outline sectional view showing the production process of the semiconductor device concerning the gestalt 2 of operation of the invention in this application.
- [Drawing 5] It is the outline sectional view showing the production process of the semiconductor device concerning the gestalt 2 of operation of the invention in this application.
- [Drawing 6] It is the outline sectional view showing the production process of the semiconductor device concerning the gestalt 2 of operation of the invention in this application.
- [Drawing 7] It is the outline sectional view showing the production process of the semiconductor device concerning the gestalt 3 of operation of the invention in this application.
- [Drawing 8] It is the outline sectional view showing the production process of the semiconductor device concerning the gestalt 3 of operation of the invention in this application.
- [Drawing 9] It is the outline fragmentary sectional view showing a part of production process of the semiconductor device concerning the gestalt 3 of operation of the invention in this application.
- [Drawing 10] It is the outline sectional view showing the production process of the conventional semiconductor device.
- [Drawing 11] It is the outline sectional view showing the production process of the conventional semiconductor device.
- [Drawing 12] It is the outline sectional view of the semiconductor device for explaining the conventional trouble.
- [Description of Notations]
1. Semi-conductor Substrate
 2. Plasma
 3. Processed Film
 4. Surface Treatment Layer
 5. Antireflection Film
 6. Ozone Gas
 7. Chemistry Magnification Mold Resist
 8. Surface Treatment Layer
 10. Electrical-Potential-Difference Impression Means
 11. Excimer Laser Light

[Translation done.]

* NOTICES *


JPO and NCIPi are not responsible for any damages caused by the use of this translation.

1. This document has been translated by computer. So the translation may not reflect the original precisely.
2. **** shows the word which can not be translated.
3. In the drawings, any words are not translated.


DRAWINGS

[Drawing 1]


(a)







(b)



(c)




[Drawing 2]




[Drawing 4]

(a)




1:半導体装置 3:被加工膜
5:反射防止膜

(b)




6:オゾンガス 8:改質層

(c)




7:化学増幅型レジスト

[Drawing 6]




3a:被加工膜パターン




[Drawing 9]



[Drawing 12]




[Drawing 5]




[Drawing 7]

(a)




1: 半導体基板 3: 被加工膜
5: 反射防止膜

(b)



7: 化学増幅型レジスト


(c)



9: マスク 11: エキシマレーザー光
10: 電圧印加手段


[Drawing 8]

(a)




7:レジストパターン

(b)



5a:反射防止膜パターン


(c)




3a:被加工膜パターン

[Drawing 10]


(a)




(b)




(c)



[Drawing 11]
(a)



(b)



[Translation done.]

(19)日本国特許庁 (J P)

(12) 公開特許公報 (A)

(11)特許出願公開番号
特開2003-209046
(P2003-209046A)

(43)公開日 平成15年7月25日(2003.7.25)

(51)Int.Cl. ⁷	識別記号	F I	テマコード [*] (参考)
H 0 1 L 21/027		G 0 3 F 7/004	5 0 3 A 2 H 0 2 5
G 0 3 F 7/004	5 0 3	7/11	5 0 3 2 H 0 9 6
7/11	5 0 3	7/38	5 0 1 5 F 0 0 4
7/38	5 0 1	H 0 1 L 21/30	5 6 3 5 F 0 4 6
H 0 1 L 21/3065			5 0 2 Z

審査請求 未請求 請求項の数11 O L (全 11 頁) 最終頁に続く

(21)出願番号 特願2002-7228(P2002-7228)

(22)出願日 平成14年1月16日(2002.1.16)

(71)出願人 000006013

三菱電機株式会社

東京都千代田区丸の内二丁目2番3号

(72)発明者 川井 健治

東京都千代田区丸の内二丁目2番3号 三

菱電機株式会社内

(74)代理人 100102439

弁理士 宮田 金雄 (外1名)

最終頁に続く


(54)【発明の名称】 レジストパターン形成方法および半導体装置の製造方法

(57)【要約】


【課題】 塩基性物質を含む下地膜とその上に形成される化学増幅型レジストとの界面における酸失活現象を抑制し、塩基性物質を含む下地膜上でも精度の高いレジストパターンを形成する。

【解決手段】 塩基性物質を含む下地膜表面をカーボンガスを含むガスによるプラズマを晒す表面改質処理を行う工程と下地膜上に化学増幅型レジスト膜を塗布する工程と化学増幅型レジストに露光および現像処理を行って化学増幅型レジストをパターンニングする工程とを備えるようにしたものである。

(a)


1:半導体基板 3:被加工膜
5:反射防止膜

(b)



2:プラズマ 4:改質層

(c)



1:化学増幅型レジスト

【特許請求の範囲】

【請求項 1】 塩基性物質を含む下地膜表面をカーボンを含むガスを用いたプラズマ中に晒す表面処理工程と、表面処理された前記下地膜上に化学増幅型レジストを形成する工程と、
前記化学増幅型レジストに露光および現像処理を行って前記化学増幅型レジストをパターンニングする工程とを備えたレジストパターン形成方法。

【請求項 2】 カーボンを含むガスは、フロロカーボン、ハイドロフロロカーボン、ハイドロカーボン、ヘキサメチルジシラザン、CO、CO₂、R-OH（アルコール類）の内の少なくとも一つ以上を含むガスであることを特徴とする請求項 1 記載のレジストパターン形成方法。

【請求項 3】 下地膜は、SiON、SiN、TiN、WN、Ta₂N、BN、CN、AlN、Ga₂N、GeN の内の少なくとも一つ以上を含むことを特徴とする請求項 1 記載のレジストパターン形成方法。

【請求項 4】 下地膜は、反射防止膜であることを特徴とする請求項 1 記載のレジストパターン形成方法。

【請求項 5】 塩基性物質を含む下地膜表面をオゾンガスに晒す表面処理工程と、
表面処理された前記下地膜上に化学増幅型レジスト膜を形成する工程と、
前記化学増幅型レジストに露光および現像処理を行って前記化学増幅型レジストをパターンニングする工程とを備えたレジストパターン形成方法。

【請求項 6】 塩基性物質を含む下地膜表面を酸素を含む高温ガスに晒す表面処理工程と、
表面処理された前記下地膜上に化学増幅型レジスト膜を形成する工程と、
前記化学増幅型レジストに露光および現像処理を行って前記化学増幅型レジストをパターンニングする工程とを備えたレジストパターン形成方法。

【請求項 7】 酸素を含む高温ガスは、N₂O または O₂ であることを特徴とする請求項 6 記載のレジストパターン形成方法。

【請求項 8】 基板上に塩基性物質を含む下地膜を形成する工程と、
前記下地膜上に化学増幅型レジスト膜を形成する工程と、
前記化学増幅型レジストに露光および現像処理を行って前記化学増幅型レジストをパターンニングする工程とを備えたレジストパターン形成方法であって、
電圧印加手段により前記基板に電位を与え前記下地膜を分極させた状態で前記露光を行うことを特徴とするレジストパターン形成方法。

【請求項 9】 電圧印加手段は、高周波電圧であることを特徴とする請求項 8 記載のレジストパターン形成方法。

【請求項 10】 電圧印加手段は、基板が載置されたステージを介して該基板に電位を与えることを特徴とする請求項 8 記載のレジストパターン形成方法。

【請求項 11】 請求項 1 ないし 10 記載のレジストパターン形成方法を用いて形成されたレジストパターンを用いて、下地膜をエッチングする工程を備えた半導体装置の製造方法。

【発明の詳細な説明】

【0001】

【発明の属する技術分野】 本発明は、レジストパターン形成方法およびこれを用いた半導体装置の製造方法に関し、特に、塩基性物質を含む下地膜上に化学増幅型レジストを精度良くパターンニングするためのレジストパターン形成方法およびこの方法を用いた半導体装置の製造方法に関するものである。

【0002】

【従来の技術】 図 10 および図 11 は、化学増幅型レジストを用いた従来の半導体装置の製造方法を示す断面図である。図 10 (a) を参照して、半導体基板 101 上に被加工膜 103、反射防止膜 105 およびボジ型の化学増幅型レジスト 107 を順次形成する。次に、図 10 (b) を参照して、半導体基板 101 上に所望のパターンを配したフォトマスク 109 を介してエキシマレーザー光 111 を照射し、化学増幅型レジスト 107 を露光する。このとき、化学増幅型レジスト 107 内では光が照射された露光部 107a にプロトン酸である H⁺ が発生する。このプロトン酸はレジスト樹脂などが化学変化を起こす触媒として作用し、現像液に溶解する物質へと変化させる。

【0003】 次に、図 10 (c) を参照して、露光された化学増幅型レジスト 107 を現像することによって露光部 107a を溶解し、未露光部 107b が残存することでレジストパターン 107c が形成される。次に、図 11 (a) を参照して、レジストパターン 107c をマスクとして、反射防止膜 105 をエッチングすることにより、反射防止膜パターン 105b を形成する。

【0004】 次に、図 11 (b) を参照して、レジストパターン 107c および反射防止膜パターン 105b をマスクに被加工膜 103 をエッチングし、所望の被加工膜パターン 103a を得る。その後、レジストパターンを除去し、所定のプロセスを経て所望の半導体装置が完成する。

【0005】

【発明が解決しようとする課題】 しかしながら、上記のような従来技術においては、化学増幅型レジストの下地膜である反射防止膜が電子を与えやすい塩基性物質を含んでいると、図 12 に示すように、レジストと反射防止膜との界面において、レジストで発生したプロトン酸 (H⁺) が反射防止膜から供給された電子と中和反応を起こす、いわゆる酸失活現象によりレジストの現像液へ

の溶解性が低下する。

【0006】その結果、図10(c)に示すように、レジストパターン107cの下部が裾を引いたような形状となる。このようなレジストパターンをマスクに被加工膜をエッチングすると、被加工膜パターンが所望の寸法よりも太くなったり、肩が落ちたような段ずれ形状となり、寸法精度の制御が困難になるという問題点があった。なお、上述した化学増幅型レジストはポジ型（露光部が現像液に溶解する）を想定したが、ネガ型（未露光部が現像液に溶解する）の場合には、レジストパタンの下部が逆に細くなり、その結果、レジストパターンが倒れやすくなったり、被加工膜パターンが細くなるなど、同様の問題点があった。

【0007】本願発明は、上記のような問題を解消するためになされたもので、第1の目的は、塩基性物質を含む下地膜上でも、精度の良いレジストパターンを形成できるレジストパターン形成方法を提供するものである。

【0008】また、第2の目的は、上記レジストパターン形成方法を用いた半導体装置の製造方法を提供するものである。

【0009】

【課題を解決するための手段】塩基性物質を含む下地膜表面をカーボンを含むガスをを用いたプラズマ中に晒す表面処理工程と表面処理された下地膜上に化学増幅型レジストを形成する工程と化学増幅型レジストに露光および現像処理を行って化学増幅型レジストをパターンニングする工程とを備えるようにしたものである。

【0010】また、カーボンを含むガスは、フロロカーボン、ハイドロフロロカーボン、ハイドロカーボン、ヘキサメチルジシラザン、CO、CO₂、R-OH（アルコール類）の内の少なくとも一つ以上を含むガスとしたものである。

【0011】また、下地膜は、SiON、SiN、TiN、WN、Ta₂N、BN、CN、AlN、GaN、GeNの内の少なくとも一つ以上を含むようにしたものである。

【0012】また、下地膜は、反射防止膜としたものである。

【0013】また、塩基性物質を含む下地膜表面をオゾンガスに晒す表面処理工程と表面処理された下地膜上に化学増幅型レジスト膜を形成する工程と化学増幅型レジストに露光および現像処理を行って化学増幅型レジストをパターンニングする工程とを備えるようにしたものである。

【0014】また、塩基性物質を含む下地膜表面を酸素を含む高温ガスに晒す表面処理工程と表面処理された下地膜上に化学増幅型レジスト膜を形成する工程と化学増幅型レジストに露光および現像処理を行って化学増幅型レジストをパターンニングする工程とを備えるようにしたものである。

【0015】また、酸素を含む高温ガスは、N₂OまたはO₂としたものである。

【0016】また、基板上に塩基性物質を含む下地膜を形成する工程と下地膜上に化学増幅型レジスト膜を形成する工程と化学増幅型レジストに露光および現像処理を行って化学増幅型レジストをパターンニングする工程とを備え、電圧印加手段により基板に電位を与え下地膜を分極させた状態で露光を行うようにしたものである。

【0017】また、電圧印加手段は、高周波電圧としたものである。

【0018】また、電圧印加手段は、基板が載置されたステージを介して該基盤に電位を与えるようにしたものである。

【0019】また、上記方法を用いて、下地膜をエッチングするものである。

【0020】

【発明の実施の形態】実施の形態1. 図1ないし図3は、本願発明の実施の形態1に係る半導体装置の製造工程を示す概略断面図である。なお、以下の説明において、同一又は相当部分には同一の符号を付してその説明を省略する。

【0021】図1(a)を参照して、半導体基板1上に、減圧CVD法により、SiH₄（シラン）とH₂（水素）の混合ガスまたはSiH₄とN₂（窒素）の混合ガスをを用いて、600℃～700℃の形成温度条件下で、ポリシリコンからなる被加工膜3を形成する。このとき、不純物源としてPH₃、AsH₃を用い、熱処理により不純物を拡散するようにしてもよい。次に、この被加工膜3の上に、プラズマCVD法により、SiH₄、NH₃（アンモニア）およびN₂O（一酸化二窒素）の混合ガスをを用いて、300℃～450℃の形成温度条件下で、塩基性を示す物質、例えば、Nを含むSiON（酸化シリコン）からなる反射防止膜5を形成する。

【0022】塩基性を示す反射防止膜5としては、上記のSiONの他に、SiN（窒化シリコン）、TiN（窒化チタン）などを用いてもよい。SiNは、プラズマCVD法により、SiH₄、NH₃およびH₂の混合ガスをを用いて、300℃～450℃の形成温度条件下で形成される。

【0023】次に、図1(b)を参照して、C（カーボン）を含むガスをプラズマ化し、このプラズマ2に半導体基板1を晒すことにより反射防止膜5の表面を改質する。プラズマ2は、ICP型プラズマ反応装置や2周波平行平板型プラズマ反応装置を用いて、1.33Pa～133Paの圧力下でCを含むガスを放電させて形成する。プラズマ2に晒す時間は5秒～30秒間程度である。この表面処理により、反射防止膜5の表面には、厚さ1～20nmのCF系ポリマー（C、F_y）からなる改質層4が形成される。

【0024】Cを含むガスとしては、例えば、フロロカーボン系ガス、ハイドロフロロカーボン系ガス、ハイドロカーボン系ガス、HMDS（ヘキサメチルジシラザン： $(\text{CH}_3)_3\text{Si})_2\text{NH}$ ）、 CO （炭酸ガス）、 CO_2 （二酸化炭素）、 R-OH （アルコール類）[R：アルキル基]を少なくとも一つ以上含むガスを用いる。

【0025】ここで、フロロカーボン系ガスとは、 CF_4 （テトラフロロメタン）、 C_4F_8 （オクタフロロシクロブタン）、 C_5F_8 （オクタフロロシクロペンテン）、 C_4F_6 （ヘキサフロロー1、3-ブタジエン）、 C_2F_6 （ヘキサフロロエタン）、 C_3F_8 （オクタフロロプロパン）などである。また、ハイドロフロロカーボン系ガスとは、 CHF_3 （トリフロロメタン）、 CH_2F_2 （ジフロロメタン）、 CH_3F （モノフロロメタン）などである。また、ハイドロカーボン系ガスとは、 CH_4 （メタン）、 C_2H_2 （アセチレン）、 C_2H_4 （エチレン）などである。

【0026】次に、図1(c)を参照して、表面に改質層4が形成された反射防止膜5上に膜厚500nmの化学増幅型レジスト膜7を形成する。化学増幅型レジスト膜7として、市販のポジ型レジスト（TDUR-P015：東京応化工業製）を用いた。次に、図2(a)を参照して、所望のパターンを配したフォトマスク9を介して半導体基板1上に、 KrF （波長248nm）や ArF （波長193nm）などのエキシマレーザー光11を照射し、化学増幅型レジスト7を露光する。

【0027】このとき、レジストの露光部分7aでは化学変化を促進させる触媒としてプロトン酸（ H^+ ）が生じるが、下地膜である反射防止膜5の表面に形成された改質層4が反射防止膜5からの電子の供給をブロックするブロック層となってレジストと反射防止膜との界面における中和反応（酸失活現象）を抑制する。

【0028】その結果、図2(b)を参照して、その後の現像処理において、露光部分7aの現像液への溶解性が向上し、未露光部分7bが残存して形成されるレジストパターン7cは裾引きのない良好な形状となる。また、上記のような表面処理により反射防止膜表面が疎水性となり、レジストと反射防止膜との密着性も向上する。

【0029】次に、図2(c)を参照して、レジストパターン7cをマスクに、2周波平行平板型エッチング装置により、10mTorr～800mTorrの圧力に制御された CF_4 、 O_2 、および Ar の混合ガスのプラズマを用いて、改質層4および反射防止膜5をエッチングし反射防止膜パターン5aを形成する。なお、上記混合ガスにさらに CHF_3 ガスを添加した混合ガスを用いてもよい。

【0030】次に、図3を参照して、レジストパターン7cおよび反射防止膜パターン5aをマスクに、ICP

型またはECR型エッチング装置により、0.2～10Paの圧力に制御された Cl_2 と O_2 の混合ガスまたは HBr と O_2 の混合ガスのプラズマを用いて被加工膜3をエッチングし、被加工膜パターン3aを形成する。その後、不要となったレジストパターン7cを除去し、所定の工程を経て所望の半導体装置が完成する。

【0031】以上のように、実施の形態1に係る発明によれば、化学増幅型レジストが形成されるべき下地となる塩基性物質を含む反射防止膜表面を、Cを含むガスを用いたプラズマに晒すことにより、化学増幅型レジストパターン形成における露光の際に反射防止膜と化学増幅型レジストとの界面における中和反応が抑制されるので良好な形状を有したレジストパターンが得られる。

【0032】また、上記プラズマ処理により化学増幅型レジストと反射防止膜との密着性が向上するのでレジスト剥れを防止することができる。その結果、化学増幅型レジストパターンをマスクにした被加工膜のエッチング制御性が向上し、寸法精度制御性の高い良好な被加工膜パターンを有した半導体装置を製造することができる。

【0033】実施の形態2、実施の形態1では、塩基性物質を含む下地膜にCを含むプラズマ処理を施してその表面を改質したが、本実施の形態はプラズマよりもダメージが少ない表面処理方法に関するものである。図4ないし図6は、本願発明の実施の形態2に係る半導体装置の製造工程を示す概略断面図である。以下、これらの図を用いて詳細に説明する。

【0034】図4(a)を参照して、実施の形態1と同様に、半導体基板1上にポリシリコンからなる被加工膜3および下地膜として、塩基性物質を含む SiON などの反射防止膜5を順次形成する。次に、図4(b)を参照して、半導体基板1上の反射防止膜5の表面を O_3 （オゾン）ガス6に晒し、反射防止膜5の表面を改質する。

【0035】 O_3 ガス6は、所定の処理装置を用いて、20℃～200℃の温度に設定したステージ上に半導体基板1を載置し、装置内の圧力を100mTorr～10Torrに保った状態で、オゾネーターで発生したオゾンガスを排気の力で半導体基板1の表面まで導入される。このような表面処理により反射防止膜5の表面には、厚さ1nm～10nmの酸化膜（ SiO_x （ $0 < x < 2$ ））からなる改質層8が形成される。

【0036】次に、図4(c)を参照して、表面に改質層8が形成された反射防止膜5上に膜厚500nmのポジ型の化学増幅型レジスト膜7を形成する。次に、図5(a)を参照して、所望のパターンを配したフォトマスク9を介して半導体基板1上に、 KrF （248nm）や ArF （193nm）などのエキシマレーザー光11を照射し、化学増幅型レジスト7を露光する。

【0037】このとき、レジストの露光部7aでは化学変化を促進させる触媒としてプロトン酸（ H^+ ）が生じ

るが、下地膜である反射防止膜 5 の表面に形成された改質層 8 が反射防止膜 5 からの電子の供給をブロックするブロック層となってレジストと反射防止膜との界面における中和反応（酸失活現象）が抑制される。

【0038】その結果、図 5（b）を参照して、その後の現像処理において、露光部 7 a の現像液への溶解性が向上し、未露光部 7 b が残存して形成されるレジストパターン 7 c は裾引きのない良好な形状となる。また、ガス雰囲気半導体基板を晒すだけなので、プラズマ処理を施した時のようにプラズマによるチャージアップダメージが少なく、ゲート絶縁膜などの破壊を防止することができる。

【0039】以下、実施の形態 1 の場合と同様に、図 5（c）を参照して、レジストパターン 7 c をマスクに、改質層 8 および反射防止膜 5 をエッチングし、反射防止膜パターン 5 a を形成する。その後、図 6 を参照して、レジストパターン 7 c および反射防止膜パターン 5 a をマスクに、被加工膜 3 をエッチングし、被加工膜パターン 3 a を形成する。最後に、不要となったレジストパターン 7 c を除去し、所定の工程を経て半導体装置が完成する。

【0040】以上のように、実施の形態 2 に係る発明によれば、化学増幅型レジストが形成されるべき下地となる塩基性物質を含む反射防止膜表面を、 O_3 ガスに晒すことにより、化学増幅型レジストパターン形成時の露光の際に反射防止膜と化学増幅型レジストとの界面における中和反応が抑制され良好な形状を有したレジストパターンが得られる。その結果、このレジストパターンをマスクにした被加工膜のエッチング制御性が向上し、寸法精度制御性の高い良好な被加工膜パターン形状を有した半導体装置を製造することができる。

【0041】また、改質層は O_3 ガスに晒すだけで形成されるので、プラズマ処理を施した時にようにプラズマによるチャージアップダメージを低減でき信頼性の高い半導体装置を製造することができる。

【0042】実施の形態 3、実施の形態 2 では化学増幅型レジストの下地である反射防止膜表面をオゾンガスによって改質したが、本実施の形態では、オゾンガスの代わりに、酸素を含む N_2O や O_2 などの高温ガスを用いる。その他の工程は実施の形態 2 と同様である。このような高温ガスは、所定の処理装置を用いて、ステージ上に半導体基板 1 を載置し、装置内の圧力を $1.00\text{ mTorr} \sim 1.0\text{ Torr}$ に保った状態で、反応炉で $600^\circ\text{C} \sim 1000^\circ\text{C}$ の高温に加熱した上記ガスを排気の力で半導体基板 1 の表面まで導入される。

【0043】以上のように、実施の形態 3 に係る発明によれば、化学増幅型レジストが形成されるべき下地となる塩基性物質を含む反射防止膜表面を、酸素を含む N_2O や O_2 ガスなどの高温ガスに晒すことにより、化学増幅型レジストパターン形成時の露光の際に反射防止膜と

化学増幅型レジストとの界面における中和反応が抑制され良好な形状を有したレジストパターンが得られる。その結果、このレジストパターンをマスクにした被加工膜のエッチング制御性が向上し、寸法精度制御性の高い良好な被加工膜パターン形状を有した半導体装置を製造することができる。

【0044】さらに、改質層は N_2O や O_2 ガスに晒すだけで形成されるので、プラズマ処理を施した時にようにプラズマによるチャージアップダメージを低減でき信頼性の高い半導体装置を製造することができる。

【0045】実施の形態 4、実施の形態 1 ないし 3 では、塩基性物質を含む下地膜表面に改質層を形成し、下地膜からレジストへの電子の供給をブロックすることにより中和反応を抑制したが、本実施の形態では、半導体基板に電気的作用を与えることによって、下地膜との界面付近に発生するレジスト中のプロトン酸 (H^+) の中和反応を抑制するものである。

【0046】図 7 および図 8 は、本願発明の実施の形態 3 に係る半導体装置の製造工程を示す概略断面図である。図 7（a）を参照して、半導体基板 1 上にポリシリコンからなる被加工膜 3 および下地膜として、塩基性物質を含む $SiON$ などの反射防止膜 5 を順次形成する。次に、図 7（b）を参照して、反射防止膜 5 上に化学増幅型レジスト膜 7 を形成する。

【0047】次に、図 7（c）を参照して、所望のパターンを配したフォトマスク 9 を介して半導体基板 1 上に、 $KrF(248\text{ nm})$ や $ArF(193\text{ nm})$ などのエキシマレーザー光 11 を照射して化学増幅型レジスト 7 を露光する。このとき、半導体基板 1 には電圧印加手段 10 によって所定の正電位が与えられている。電位は、半導体基板 1 に直接与えてもよいし、半導体基板 1 が載置される半導体製造装置等のステージに電圧を印加することで間接的に与えてもよい。

【0048】図 9 は半導体基板に正電位を与えた場合における反射防止膜 5 中の電荷の様子を模式的に示す半導体装置の部分断面図である。図 9 を参照して、半導体基板 1 に正電位が与えられると、反射防止膜 5 中の電荷が分極し、表面には正の電荷、その対向面には負の電荷（電子）が集まる。この状態で、化学増幅型レジスト 7 が露光されると露光部 7 a には化学反応を促進させる触媒としてプロトン酸 (H^+) が発生する。一方、塩基性の反射防止膜 5 はその中の電子が上述のように分極して、いわばトラップされた状態となり、電子を供与する塩基性の性質が弱まる。

【0049】その結果、反射防止膜 5 からの電子の供給が減少し、レジスト中のプロトン酸 (H^+) と電子との中和反応が抑制され、図 8（a）に示すように、その後の現像処理において、露光部 7 a の現像液への溶解性が向上し、未露光部 7 b が残存して形成されるレジストパターン 7 c は裾引きのない良好な形状となる。

【0050】以下、実施の形態1と同様に、図8(b)を参照して、レジストパターン7cをマスクに反射防止膜5をエッチングし、反射防止膜パターン5aを形成する。次に、図8(c)を参照して、レジストパターン7cおよび反射防止膜パターン5aをマスクに被加工膜3をエッチングし、被加工膜パターン3aを形成する。その後、不要となったレジストパターン7cを除去し、所定の工程を経て半導体装置が完成する。

【0051】なお、電圧印加手段10によって与えられる正電位は、あまり強すぎると反射防止膜表面に分極して集まった正電荷によりレジスト中のプロトン酸 (H^+) が反発されレジスト底部における触媒反応が低下するので却って形状が悪化する恐れがある。したがって、与えられる正電位は、電子をトラップできる程度に大きく、プロトン酸 (H^+) を反発しない程度に小さな電位である必要があり、+100V~1000Vの電位が望ましい。

【0052】また、上述の例では印加電圧が正の直流電圧であったが、高周波電圧を印加しプロトン酸 (H^+) がレジスト露光部7a中を上下に振動しながら反射防止膜との界面付近に移動するようにしても同様の効果を奏する。高周波としては、プロトン酸である H^+ イオンが追隨する、100kHz~20MHzであることが望ましい。

【0053】以上のように、実施の形態4に係る発明によれば、半導体基板に正電位を与えることによって反射防止膜中の電子がトラップされ反射防止膜の電子を供給する塩基性としての性質が弱まるので、化学増幅型レジスト中のプロトン酸 (H^+) の失活が抑制され良好な形状を有したレジストパターンが得られる。その結果、このレジストパターンをマスクにした被加工膜のエッチング制御性が向上し、寸法精度制御性の高い良好な被加工膜パターン形状を有した半導体装置を得ることができる。

【0054】なお、上述した各実施の形態では、塩基性を示す下地膜が反射防止膜である場合を想定したが必ずしもこれに限られるものではなく、塩基性物質を含み塩基性を示す下地膜であればどのような下地膜上でも適用することが可能である。例えば、バリアメタル膜としてのTiN、WN（窒化タンゲステン）、TaN（窒化タンタル）、またそれ以外の用途の膜としてBN（窒化ボロン）、CN（窒化炭素）、AlN（窒化アルミニウム）、GaN（窒化ガリウム）、GeN（窒化ゲルマニウム）などのNを含む材料上でも適用が可能である。また、化学増幅型レジストはポジ型である場合を想定したが、ネガ型であっても同様の効果を奏することは言うまでもない。

【0055】

【発明の効果】この発明は、以上のように構成されているので以下に示すような効果を奏する。請求項1に係る

発明によれば、塩基性物質を含む下地膜表面をカーボンを含むガスプラズマで表面処理するので、その上に形成される化学増幅型レジストを精度良くパターンニングすることができる。

【0056】また、請求項2に係る発明によれば、さらに、下地膜と化学増幅型レジストとの密着性が向上し、レジスト剥れを防止することができる。

【0057】また、請求項3に係る発明によれば、SiON、SiN、TiN、WN、Ta₂N、BN、CN、AlN、GaN、GeNのような下地膜上でも、精度の高いレジストパターンを形成することができる。

【0058】また、請求項4に係る発明によれば、さらに、露光の反射を防止できるのでより精度の高いレジストパターンを形成することができる。

【0059】また、請求項5に係る発明によれば、塩基性物質を含む下地膜表面をオゾンガスに晒すので、その上に形成される化学増幅型レジストを精度良くパターンニングすることができる。とともに、下地膜へのダメージを少なくすることができるので信頼性の高いパターンニングをすることができる。

【0060】また、請求項6に係る発明によれば、塩基性物質を含む下地膜表面を酸素を含む高温ガスに晒すので、その上に形成される化学増幅型レジストを精度良くパターンニングすることができる。とともに、下地膜へのダメージを少なくすることができるので信頼性の高いパターンニングをすることができる。

【0061】また、請求項7に係る発明によれば、高温ガスとしてN₂OまたはO₂のような簡易なガスを用いて、化学増幅型レジストを精度よく形成できる。

【0062】また、請求項8に係る発明によれば、基板に正電位を与えて塩基性物質を含む下地膜を分極するので、その上に形成される化学増幅型レジストを精度良くパターンニングすることができる。

【0063】また、請求項9に係る発明によれば、さらに、印加電圧の制御性が向上するので、安定した化学増幅型レジストのパターンニングをすることができる。

【0064】また、請求項10に係る発明によれば、既存の半導体製造装置を用いて、精度の良い化学増幅型レジストのパターンニングをすることができる。

【0065】また、請求項11に係る発明によれば、精度のよいレジストパターンをマスクに被加工膜をエッチングすることができるので、被加工膜のエッチング制御性が向上し、寸法精度制御性の高い良好な被加工膜パターン形状を有した半導体装置を得ることができる。

【図面の簡単な説明】

【図1】 本願発明の実施の形態1に係る半導体装置の製造工程を示す概略断面図である。

【図2】 本願発明の実施の形態1に係る半導体装置の製造工程を示す概略断面図である。

【図3】 本願発明の実施の形態1に係る半導体装置の

11

製造工程を示す概略断面図である。

【図4】 本願発明の実施の形態2に係る半導体装置の製造工程を示す概略断面図である。

【図5】 本願発明の実施の形態2に係る半導体装置の製造工程を示す概略断面図である。

【図6】 本願発明の実施の形態2に係る半導体装置の製造工程を示す概略断面図である。

【図7】 本願発明の実施の形態3に係る半導体装置の製造工程を示す概略断面図である。

【図8】 本願発明の実施の形態3に係る半導体装置の製造工程を示す概略断面図である。

【図9】 本願発明の実施の形態3に係る半導体装置の製造工程の一部を示す概略部分断面図である。

【図10】 従来の半導体装置の製造工程を示す概略断面図である。

*

12


*【図11】 従来の半導体装置の製造工程を示す概略断面図である。

【図12】 従来の問題点を説明するための半導体装置の概略断面図である。


【符号の説明】

- 1. 半導体基板
- 2. プラズマ
- 3. 被加工膜
- 4. 表面改質層
- 5. 反射防止膜
- 6. オゾンガス
- 7. 化学増幅型レジスト
- 8. 表面改質層
- 10. 電圧印加手段
- 11. エキシマレーザー光


【図1】



【図2】




【図3】




3a:被加工膜パターン

(b)

【図4】


1:半導体装置 3:被加工膜
5:反射防止膜

【図6】




3a:被加工膜パターン

(c)




6:オゾンガス 8:改質層




7:化学増幅型レジスト


【図9】

5:反射防止膜 7a:露光部
7b:未露光部 10:電圧印加手段


【図12】



【図5】




【図7】




【図8】

(a)




7:レジストパターン

(b)



5a:反射防止膜パターン


(c)




3a:被加工膜パターン

【図10】


(a)



(b)




(c)




【図11】

(a)



(b)



フロントページの続き

(51)Int.Cl.⁷

識別記号

F I
H O I L 21/302

テーマコード(参考)

H

F ターム(参考) 2H025 AA03 AA04 AB16 AC04 AD01
 AD03 BE00 BE10 DA34 FA17
 2H096 AA25 BA01 BA09 CA06 CA20
 DA03 EA03 EA04 GA08 LA30
 5F004 DA01 DA02 DA03 DA15 DA16
 DB07 DB08 DB12
 5F046 CC01 HA05 HA07